

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-295936

(43)Date of publication of application : 12.11.1996

---

(51)Int.Cl.

G21D 8/12

G22C 38/00

G22C 38/48

H01F 1/16

---

(21)Application number : 07-098902

(71)Applicant : NIPPON STEEL CORP

(22)Date of filing : 24.04.1995

(72)Inventor : SHIMAZU TAKAHIDE  
MUNETA KOUJI

---

## (54) PRODUCTION OF NONORIENTED SILICON STEEL SHEET EXCELLENT IN SURFACE PROPERTY AND MAGNETIC PROPERTY

### (57)Abstract:

**PURPOSE:** To produce a nonoriented silicon steel sheet excellent in surface properties, brittleness, magnetic flux density and core loss by subjecting an extra low carbon-high Si hot rolled steel sheet having a specified compsn. contg. Sn, Cu, Ni, Cr, C and Nb to specified hot rolled sheet annealing, cooling treatment, cold rolling and recrystallization annealing.

**CONSTITUTION:** A hot rolled steel sheet having a compsn. contg., by weight, <0.005% C, 2.0 to 4.0% Si, 0.05 to 2% Al, 0.05 to 1.5% Mn, ≤0.1% P, ≤0.003% S, <0.004% N, 0.003 to 0.2% Sn, 0.015 to 0.2% Cu, 0.01 to 0.2% Ni, 0.02 to 0.2% Cr, 0.0005 to 0.008% V, <0.001% Nb, and the balance inevitable components is subjected to hot rolled sheet annealing to regulate the grain size to ≥ 50μm and is gradually cooled at ≤80° C/sec. This hot rolled steel sheet is subjected to cold rolling at 288% rolling ratio. After that, this cold rolled sheet is subjected to recrystallization annealing at 800 to 1200° C. Thus, the nonoriented silicon steel sheet of a high grade can be obt'd., and the way of largely consuming inexpensive iron scraps is developed.